

MATERIAL DATA SHEETS

PROPERTIES	UNITS	ASTM TEST METHOD	NYLON 6/6 (MOLDED)	NYLON 6/6 30% GLASS-FILLED	POLYETHYLENE	POLYPROPYLENE
Tensile strength at yield	psi Mpa	D-638	9000 62	25,000 172	5800 40	4000 28
Elongation at yield at fail	% %	D-638	20 200	5-10 40	NR 600	18 150
Flexural Modulus at yield	10 ³ psi Mpa	D-790	190 1310	800-900 5516-6206	NR	150 1030
Isod impact strength notched	ft-lb/in joules/M	D-256	3.0 160	2 107	NR	2.0 107
Deflection temp. at 66 psi at 264 psi	°F (°C) °F (°C)	D-648	430 160 (71)	500 (260) 485-490 (251-255)	NR	194 (90) 150 (65)
Melting point	°F °C	D-789	482 250	500-509- 260-265 T _m	NR	340 171
Dielectric strength	V/mil	D-149	550	500	500-900	650
Volume resistivity	ohm-cm	D-257	2 x 10E+13	1 x 10E+15	1 x 10E+16	1 x 10E+17
Water absorption	%/24hr.	D-570	1.1	0.9	NR	0.01
UL flammability	---	UL 94	94 V-2	94 HB	NR	94 HB
Rockwell Hardness	---	R, M scales	R105	M96	NR	R85
Flexural strength	10 ³ psi Mpa	D-638	17.9 123	36-38 255	NR	7000 48
Thermal conductivity	Btu-in/hr-ft ² -°F W/m-°C	---	1.7 .25	1.4-1.5 .20-.22	2.9-3.5 .42-50	.81 .12
Specific Gravity	---	D-792	1.16	1.37-1.39	1.09	.09
Max. service temperature	°F °C	---	221 105	230-240 110-116	212 100	212 100

NR: Not Reported

PLEASE NOTE: To the best of our knowledge, the information contained in this guide is accurate, is based upon accepted technical practices and is believed to be reliable. Final determination of suitability of any process or material is the sole responsibility of the user. **China Plastic Screw, Corp.** does not assume any liability for the accuracy or completeness of this information.

MATERIAL DATA SHEETS

PROPERTIES	UNITS	ASTM TEST METHOD	PVC	ISOPLAST POLYURETHANE 40% LONG GLASS FILLED	ULTEM 1000	ULTEM 2300 30% GLASS FILLED
Tensile strength at yield	psi Mpa	D-638	7450 51	27,000 190	15,200 105	24,500* 160*
Elongation at yield at fail	% %	D-638	NR 40-80	2 2	7-8 60	N.A. 3
Flexural Modulus at yield	10 ³ psi Mpa	D-790	400 2760	1500 10,000	480 3300	1300 9000
Isod impact strength notched	ft-lb/in joules/M	D-256	>5. >270	8 430	1 50	2.0 110
Deflection temp. at 66 psi at 264 psi	°F (°C) °F (°C)	D-648	NR 170 (77)	NR 210 (99)	410 (210) 392 (200)	412 (212) 410 (210)
Melting point	°F °C	D-789	193-246 75-105 T _g	366 (Vicat) 186	338 (Vicat) 170	356 (Vicat) 180
Dielectric strength	V/mil	D-149	1413	500	830	770
Volume resistivity	ohm-cm	D-257	1.2 x 10E+12	NR	6.7 x 10E+17	3.0 x 10E+16
Water absorption	%/24hr.	D-570	0.05	0.14	0.25	0.16
UL flammability	---	UL 94	94 V-0	94 HB	94 V-0	94 V-0
Rockwell Hardness	---	R, M scales	R115	R119	M109	M114
Flexural strength	10 ³ psi Mpa	D-638	14.45 99.63	40 275	22 150	33 230
Thermal conductivity	Btu-in/hr-ft ² -°F W/m-°C	---	.96 .14	NR NR	1.5 .22	1.6 2.3
Specific Gravity	---	D-792	1.37	1.5	1.27	1.51
Max. service temperature	°F °C	---	140 60	197 92	338 170	342 172

NR: Not Reported

PLEASE NOTE: To the best of our knowledge, the information contained in this guide is accurate, is based upon accepted technical practices and is believed to be reliable. Final determination of suitability of any process or material is the sole responsibility of the user. . does not assume any liability for the accuracy or completeness of this information.

MATERIAL DATA SHEETS

PROPERTIES	UNITS	ASTM TEST METHOD	ACETAL	POLYCAR- BONATE	PVDF (KYNAR®)	PTFE (TEFLON®)
Tensile strength at yield	psi Mpa	D-638	9700-10,000 68	9000 62	5000-7000 34-48	3000 21
Elongation at yield at fail	% %	D-638	NR 4	100-130 135	NR 50-250	NR 300
Flexural Modulus at yield	10 ³ psi Mpa	D-790	380-430 2620-2965	340-350 2344-2413	170-325 1172-2240	500 3447
Isod impact strength notched	ft-lb/in joules/M	D-256	1.2-2.3 64-123	17 908	20-80 1068-4270	3.0 160
Deflection temp. at 66 psi at 264 psi	°F (°C) °F (°C)	D-648	330-342 (165-172) 270-277 (132-136)	300-305 (149-152) 290-295 (143-146)	234-284 (112-140) 176-194 (80-90)	260 (127) 132 (55)
Melting point	°F °C	D-789	347-358 175-181 T _m	284-302 140-150 T _G	330 165	612 322
Dielectric strength	V/mil	D-149	500	380-399	260	600
Volume resistivity	ohm-cm	D-257	>1 x 10E+15	>1 x 10E+16	1 x 10E+12- 1 x 10E+14	>1 x 10E+18
Water absorption	%/24hr.	D-570	.21-.25	0.15	<0.05	<.01
UL flammability	---	UL 94	94 HB	94 V-2	94 V-0	94 V-0
Rockwell Hardness	---	R, M scales	M90-M94	R118	R79-83	R58
Flexural strength	10 ³ psi Mpa	D-638	13.6-14.1 95	14-14.2 97	6.5-9.0 45-62	No Break
Thermal conductivity	Btu-in/hr- ft ² -°F W/m-°C	---	1.6 .23	1.3 .19	.87 .13	1.7 .25
Specific Gravity	---	D-792	1.42	1.2	1.75	2.2
Max. service temperature	°F °C	---	195 91	212 100	300 150	500 260

NR: Not Reported

PLEASE NOTE: To the best of our knowledge, the information contained in this guide is accurate, is based upon accepted technical practices and is believed to be reliable. Final determination of suitability of any process or material is the sole responsibility of the user. **China Plastic Screw, Corp.** does not assume any liability for the accuracy or completeness of this information.